

# RO MEMBRANE TROUBLESHOOTING MATRIX

Possible Cause	Possible Location	Pressure Drop	Feed Pressure	Salt Passage	Suggested Products
<b>Metal Oxide Fouling</b> (e.g. Fe, Mn, Cu, Ni, Zn)	1st stage lead elements	Rapid increase	Rapid increase	Rapid increase	S-200
<b>Colloidal Fouling</b> (organic and/or inorganic complexes)	1st stage lead elements	Gradual increase	Gradual increase	Slight increase	F-25
<b>Mineral Scaling</b> (e.g. Ca, Mg, Ba, Sr)	Last stage tail elements	Moderate increase	Slight increase	Marked increase	S-200
<b>Polymerized Silica</b>	Last stage tail elements	Normal to increased	Increased	Normal to increased	S-200
<b>Biological Fouling</b>	Any stage, usually lead elements	Marked increase	Marked increase	Normal to increased	F-25
<b>Organic Fouling</b> (dissolved NOM)	All stages	Gradual increase	Increased	Decreased	F-25
<b>Oxidant Damage</b> (e.g. Cl <sub>2</sub> , ozone, KMnO <sub>4</sub> )	1st stage most severe	Normal to decreased	Decreased	Increased	N/A
<b>Hydrolysis Damage</b> (out of range pH)	All stages	Normal to decreased	Decreased	Increased	N/A
<b>Abrasion Damage</b> (carbon fines, etc)	1st stage most severe	Normal to decreased	Decreased	Increased	N/A
<b>O-ring Leaks</b> (at interconnectors or adapters)	Random (typically at feed adapter)	Normal to decreased	Normal to decreased	Increased	N/A

**NOTE:** Pressure drop is defined as the feed pressure minus the concentrate pressure. For reference only. Actual membrane analysis must be conducted for accurate diagnosis.