

NF3–SERIES MEMBRANE ELEMENTS

AXEON® NF3–Series Membrane Elements are manufactured using the industry’s leading membrane film technology. These membranes offer reliability, high performance and deliver consistent results. Water treatment professionals have come to rely on the superior performance and dependability of **AXEON NF3–Series Membrane Elements**.

AXEON NF3–Series Membrane Elements are ideal for removing a high percentage of TOC and THM precursors with medium to high salt passage and medium hardness passage. **AXEON NF3–Series Membrane Elements** are an ideal choice for surface water and ground water where good organic removal is desired with partial softening.



BENEFITS

- Superior Quality and Cost Savings
- Individually Inspected, Qualified and Vacuum Tested
- Private Labeling and Customization Available
- All Industry Standard Sizes
- Nanofiltration Membrane Elements
- Improved RO System Performance

OPERATING LIMITS


- Membrane Type: Polyamide Thin-Film Composite
- Maximum Operating Temperature (°F / °C): 113 / 45
- Maximum Operating Pressure (psi / bar): 600 / 41
- pH Range, Continuous Operation^A: 2-11
- pH Range, Short Term Cleaning (30 Min.): 1-12
- Maximum Feed Silt Density Index (SDI): 5
- Chlorine / Chloramine Tolerance (ppm): 0
- Maximum Feed Flow Rate (gpm): 2.5" = 6
4.0" = 16

A. Maximum temperature for continuous operations above pH10 is 95°F / 35°C.

SPECIFICATIONS

Part Number	Description	Applied Pressure (psi / bar)	Permeate Flow Rate (gpd / m3/d)	Nominal Salt Rejection (%)
200401	NF3 – 2514	70 / 4.83	200 / 0.76	40-50
200402	NF3 – 2521	70 / 4.83	350 / 1.33	40-50
200403	NF3 – 2540	70 / 4.83	850 / 3.22	40-50
200404	NF3 – 4014	70 / 4.83	400 / 1.51	40-50
200405	NF3 – 4021	70 / 4.83	1000 / 3.79	40-50
200406	NF3 – 4040	70 / 4.83	2500 / 9.46	40-50

Warranty Evaluation Test Conditions: Permeate flow and salt rejection based on the following test conditions: 550 ppm, filtered and dechlorinated municipal tap water, 77°F / 25°C, 15% recovery and the specified operating pressure. Permeate flows for warranty evaluation may vary -15% / +50% for 4.0" diameter elements and -20% / +30% for 2.5" diameter elements. Maximum pressure drop at 13 psig / 0.9 bar.



DIMENSIONS (IN / MM)

Description	A	B	C	D
NF3 – 2514	14 / 355.60	1.1 / 27.94	0.75 / 19.05	2.40 / 60.96
NF3 – 2521	21 / 533.40	1.1 / 27.94	0.75 / 19.05	2.40 / 60.96
NF3 – 2540	40 / 1016.00	1.1 / 27.94	0.75 / 19.05	2.40 / 60.96
NF3 – 4014	14 / 355.60	1.1 / 27.94	0.75 / 19.05	3.95 / 100.30
NF3 – 4021	21 / 533.40	1.1 / 27.94	0.75 / 19.05	3.95 / 100.30
NF3 – 4040	40 / 1016.00	1.1 / 27.94	0.75 / 19.05	3.95 / 100.30

Note: All 2514, 2521 and 2540 elements fit nominal 2.50" I.D. membrane housings and all 4014, 4021 and 4040 elements fit nominal 4.00" I.D. membrane housings.

Proper start-up of reverse osmosis water treatment systems is essential to prepare the membranes for operating service and to prevent membrane damage due to overfeeding or hydraulic shock. Before initiating system start-up procedures, membrane pretreatment, loading of the membrane elements, instrument calibration and other system checks should be completed. Avoid any abrupt pressure or cross-flow variations on the spiral elements during start-up, shutdown, cleaning or other sequences to prevent possible membrane damage. During start-up, a gradual change from a standstill to operating state is recommended as follows:

- Feed pressure should be increased gradually over a 30-60 second time frame.
- Cross-flow velocity at set operating point should be achieved gradually over 15-20 seconds.
- Permeate obtained from first hour of operation should be discarded.
- Maximum pressure drop across an entire pressure vessel (housing) is 30 psi / 2.1 bar.
- Avoid static permeate-side backpressure at all times.

Under certain conditions, the presence of free chlorine, chloramines and other oxidizing agents will cause premature membrane failure. Since oxidation damage is not covered under warranty, the manufacturer recommends removing all oxidizing agents by pretreatment prior to membrane exposure. Please contact the manufacturer or your supplier for more information.

Do not use this initial permeate for drinking water or food preparation. Keep elements moist at all times after initial wetting. To prevent biological growth during prolonged system shutdowns, it is recommended that membrane elements be immersed in a preservative solution. Rinse out the preservative before use. For membrane warranty details, please contact the manufacturer or your supplier for more information.

If operating limits and guidelines given in this product specification sheet are not strictly followed, the warranty will be null and void. The customer is fully responsible for the effects of incompatible chemicals and lubricants on elements. Use of any such chemicals or lubricants will void the warranty. These membranes may be subject to drinking water application restrictions in some countries; please check the application status before use and sale. The use of this product in and of itself does not necessarily guarantee the removal of cysts and pathogens from water. Effective cyst and pathogen reduction is dependent on the complete system design and on the operation and maintenance of the system.

No freedom from infringement of any patent owned by the manufacturer or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, customer is responsible for determining whether products and the information in this document are appropriate for customer's use and for ensuring that customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. The claims made may not have been approved for use in all countries. The manufacturer assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.